

Product: Concept Chair

COVER


Fabric | Collection: NORDIC | Cat. 4



4NA



4NB



4NC



4ND



4NE



4NF




4NG




4NH



4NJ




4NK




4NL



4NM



4NN



4NP



4NQ


Composition	Weight	Width	Martindale	Light solidity	Cleaning
50% PES - 15% PA - 35% ACRIL	410 gr/m ²	55"1/8	100.000	6	

COVER


Fabric | Collection: MOSS | Cat. 4



4MA




4MB



4MC



4MD



4ME



4MF



4MG

Composition	Weight	Width	Martindale	Light solidity	Cleaning
100% PES FR	707 gr/lm $\pm$ 5%	55"1/8	50.000 (A)	6-7	    

COVER

Fabric | Collection: CLOU | Cat. 6




H04



H05



H06



H07



H08




H09




H10



H14



H16



H17



H18




H20


Composition	Weight	Width	Martindale	Light solidity	Cleaning
48% viscose - 52% linen	610 gr/lm	55"1/8	22.000	4-5	

COVER


Leather | Collection: POLO | Cat. 7



P10



P72



P12



P30



P47



P26




P32




P31




P36




P39




P42




P44




P18




P23




P24




P25




P35



P83




P55




P56

COVER


Leather | Collection: POLO | Cat. 7




P84



P54



P58




P60

Thickness		0,9/1,1 mm	Fire resistance British Standard BS 5852 Part I (1979) N° 0: Cigarette Test N°1: Match Test passes
Origin		Raw Hides	
Place of origin		European	
Tanning		Chrome salts	
Dyeing		Aniline through - dyeing	
Finishing		Pigments finishing	
Typology		Corrected grain	
Light fastness xenon lamp	UNI EN ISO 105 B02	Value > 8 Blu scale	
Tear strenghe	UNI EN ISO 3377 - 1	42 N/mm	
Dry rub fastness	ISO 11640	500 cycles value 4/5 grey scale	
Wet rub fastness	ISO 11640	250 cycles value 4/5 grey scale	Imo FTP part 8-Resolution A652 (16) NI/0: Cigarette test NI/1: Match Test passes
Flex crack resistance	ISO 5402	> 50.000 cycles	
Adhesion of finish	UNI EN ISO 11644 2008 - Dedalo Srl (Arzignano - VI)	9 N/cm	
			TB 117-A11@2013:2013 Cigarette Test (California) passes

COVER


Leather | Collection: SAVANA | Cat. 9




961



963




964



967



968



974

Thickness	1,3/1,5 mm	
Origin	Raw Hides	
Place of origin	European	
Tanning	Chrome salts	
Dyeing	Aniline through - dyeing	
Typology	nubuck brushed by hand	
Light fastness xenon lamp	UNI EN ISO 105 B02	Value > 3 Blu scale
Tear strenghe	UNI EN ISO 3377 - 1	> 45 N
Dry rub fastness	ISO 11640	500 cycles value 4 grey scale
Wet rub fastness	ISO 11640	250 cycles value 3/4 grey scale
Flex crack resistance	ISO 5402	> 50.000 cycles
Adhesion of finish	UNI EN ISO 11644	10,5 N/cm
2008 - Dedalo Srl (Arzignano - VI)		
Fire resistance	British Standard BS 5852 Part 1 (1979) N° 0: Cigarette Test N°1: Match Test	passes

COVER


Leather I Collection: SOFT I Cat. 9



117



501



195



199




179



563



96



504




564




207




NH3




505




565




566



203




188




509



534



175




508

COVER


Leather | Collection: SOFT | Cat. 9




147



532




160



513




542



98



192




176




556




546




557



558




141



543



554



101

Thickness	1,1/1,2 mm	
Origin	Raw Hides	
Place of origin	European	
Tanning	Chrome salts	
Dyeing	Online through - dyeing	
Finishing	Water - based pigments	
Typology	Grain slightly corrected	
Light fastness xenon lamp	UNI EN ISO 105 B02	Value > 4 Blu scale
Tear strenghe	UNI EN ISO 3377 - 1	> 28 N/mm
Dry rub fastness	ISO 11640	500 cycles value 4 grey scale
Wet rub fastness	ISO 11640	80 cycles value 5 grey scale
Flex crack resistance	ISO 5402	25000 cycles
Adhesion of finish	UNI EN ISO 11644	> 7,5 N/cm
	2008 - Dedalo Srl (Arzignano - VI)	
Fire resistance	British Standard BS 5852 Part I (1979) N° 0: Cigarette Test N°1: Match Test	
	passes	

LEGS

Wood



3.011 - Oak, oiled



3.102 - Oak,
Natural stained



3.144 - Oak,
Wengé stained



3.146 - Oak,
Canaletto walnut



3.149 - Oak,
Dark grey



8.011 - Oiled
Canaletto walnut



8.146 - Natural stained
Canaletto walnut