

Product: Concept Stool

## COVER


Fabric | Collection: NORDIC | Cat. 4



4NA



4NB



4NC



4ND



4NE



4NF




4NG




4NH



4NJ




4NK




4NL



4NM



4NN



4NP



4NQ

| Composition                  | Weight                | Width  | Martindale | Light solidity | Cleaning                                                                                                                                                                                                                                                                                                                                                |
|------------------------------|-----------------------|--------|------------|----------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| 50% PES - 15% PA - 35% ACRIL | 410 gr/m <sup>2</sup> | 55"1/8 | 100.000    | 6              |     |

**Cassoni LLC**

701 Brickell Avenue, Suite 1550. Miami, FL 33131

Tel: (305) 808 9590 Fax: (305) 808 9591

contact@cassoni.com


www.cassoni.com

## COVER


### Fabric | Collection: MOSS | Cat. 4



4MA




4MB



4MC



4MD



4ME



4MF



4MG

| Composition | Weight             | Width  | Martindale | Light solidity | Cleaning |
|-------------|--------------------|--------|------------|----------------|----------|
| 100% PES FR | 707 gr/lm $\pm$ 5% | 55"1/8 | 50.000 (A) | 6-7            |          |

## COVER

### Fabric | Collection: CLOU | Cat. 6




H04



H05



H06



H07



H08




H09




H10



H14



H16



H17



H18




H20

| Composition             | Weight    | Width  | Martindale | Light solidity | Cleaning |
|-------------------------|-----------|--------|------------|----------------|----------|
| 48% viscose - 52% linen | 610 gr/lm | 55"1/8 | 22.000     | 4-5            |          |


## COVER

---


### Leather | Collection: POLO | Cat. 7



P10



P72



P12



P30



P47



P26




P32




P31




P36




P39




P42




P44




P18




P23




P24




P25




P35



P83




P55




P56

## COVER


### Leather | Collection: POLO | Cat. 7




P84



P54



P58




P60

|                           |                                                        |                                 |                                                                                                                                                    |
|---------------------------|--------------------------------------------------------|---------------------------------|----------------------------------------------------------------------------------------------------------------------------------------------------|
| Thickness                 |                                                        | 0,9/1,1 mm                      | <b>Fire resistance</b> British Standard BS 5852 Part I (1979)<br>N° 0: Cigarette Test<br>N°1: Match Test <span style="float: right;">passes</span> |
| Origin                    |                                                        | Raw Hides                       |                                                                                                                                                    |
| Place of origin           |                                                        | European                        |                                                                                                                                                    |
| Tanning                   |                                                        | Chrome salts                    |                                                                                                                                                    |
| Dyeing                    |                                                        | Aniline through - dyeing        |                                                                                                                                                    |
| Finishing                 |                                                        | Pigments finishing              |                                                                                                                                                    |
| Typology                  |                                                        | Corrected grain                 |                                                                                                                                                    |
| Light fastness xenon lamp | UNI EN ISO 105 B02                                     | Value > 8 Blu scale             |                                                                                                                                                    |
| Tear strenghe             | UNI EN ISO 3377 - 1                                    | 42 N/mm                         |                                                                                                                                                    |
| Dry rub fastness          | ISO 11640                                              | 500 cycles value 4/5 grey scale |                                                                                                                                                    |
| Wet rub fastness          | ISO 11640                                              | 250 cycles value 4/5 grey scale | Imo FTP part 8-Resolution A652 (16)<br>NI/0: Cigarette test NI/1: Match Test <span style="float: right;">passes</span>                             |
| Flex crack resistance     | ISO 5402                                               | > 50.000 cycles                 |                                                                                                                                                    |
| Adhesion of finish        | UNI EN ISO 11644<br>2008 - Dedalo Srl (Arzignano - VI) | 9 N/cm                          |                                                                                                                                                    |
|                           |                                                        |                                 | TB 117-A11@2013:2013<br>Cigarette Test ( California) <span style="float: right;">passes</span>                                                     |

## COVER

### Leather | Collection: SAVANA | Cat. 9




961



963




964



967



968



974

|                                    |                                                                                |                                 |
|------------------------------------|--------------------------------------------------------------------------------|---------------------------------|
| Thickness                          | 1,3/1,5 mm                                                                     |                                 |
| Origin                             | Raw Hides                                                                      |                                 |
| Place of origin                    | European                                                                       |                                 |
| Tanning                            | Chrome salts                                                                   |                                 |
| Dyeing                             | Aniline through - dyeing                                                       |                                 |
| Typology                           | nubuck brushed by hand                                                         |                                 |
| Light fastness xenon lamp          | UNI EN ISO 105 B02                                                             | Value > 3 Blu scale             |
| Tear strenghe                      | UNI EN ISO 3377 - 1                                                            | > 45 N                          |
| Dry rub fastness                   | ISO 11640                                                                      | 500 cycles value 4 grey scale   |
| Wet rub fastness                   | ISO 11640                                                                      | 250 cycles value 3/4 grey scale |
| Flex crack resistance              | ISO 5402                                                                       | > 50.000 cycles                 |
| Adhesion of finish                 | UNI EN ISO 11644                                                               | 10,5 N/cm                       |
| 2008 - Dedalo Srl (Arzignano - VI) |                                                                                |                                 |
| Fire resistance                    | British Standard BS 5852 Part 1 (1979) N° 0: Cigarette Test<br>N°1: Match Test | passes                          |


## COVER

---


### Leather I Collection: SOFT I Cat. 9



117



501



195



199



179



563




96



504




564




207




NH3



505




565




566




203




188




509



534



175




508

## COVER


### Leather | Collection: SOFT | Cat. 9




147




532




160



513



542




98




192




176




556




546




557




558




141



543



554



101

|                           |                                                                                |                               |
|---------------------------|--------------------------------------------------------------------------------|-------------------------------|
| Thickness                 | 1,1/1,2 mm                                                                     |                               |
| Origin                    | Raw Hides                                                                      |                               |
| Place of origin           | European                                                                       |                               |
| Tanning                   | Chrome salts                                                                   |                               |
| Dyeing                    | Online through - dyeing                                                        |                               |
| Finishing                 | Water - based pigments                                                         |                               |
| Typology                  | Grain slightly corrected                                                       |                               |
| Light fastness xenon lamp | UNI EN ISO 105 B02                                                             | Value > 4 Blu scale           |
| Tear strenghe             | UNI EN ISO 3377 - 1                                                            | > 28 N/mm                     |
| Dry rub fastness          | ISO 11640                                                                      | 500 cycles value 4 grey scale |
| Wet rub fastness          | ISO 11640                                                                      | 80 cycles value 5 grey scale  |
| Flex crack resistance     | ISO 5402                                                                       | 25000 cycles                  |
| Adhesion of finish        | UNI EN ISO 11644                                                               | > 7,5 N/cm                    |
|                           | 2008 - Dedalo Srl (Arzignano - VI)                                             |                               |
| Fire resistance           | British Standard BS 5852 Part I (1979) N° 0: Cigarette Test<br>N°1: Match Test |                               |
|                           | passes                                                                         |                               |

## BASE

---

### Steel



F047  
Matt chrome



F054 A054 F064  
Matt Black